

## UNITAN LEATHER TANNING AGENTS / Formulae

### 1. Wet Brown - Store for three months

Picked skin pH 3.8/4.0

Process for full thickness or split skin.

50%	Pickled bath	pH: 3.8/4,0 °Be: 6/8
5 - 7%	<b>UNIQUE JR</b>	
1 - 2%	Dispersant	Naftalensulphonic syntan
0.3%	Fungicide	Run 3 hs. Then Automatic Run (10'/hs) over night until complete penetration. -Drain-
30 %	Water 30°C	
2 - 3 %	Phenolic Syntan	
0.3%	Fungicide	Run 2 hs
0.5%	Formic Acid	Run 30 min

**Unload / Pile 48 hs / Drain.**

**Pile and cover with black nylon.**